


Profile	Type	Standardmaterial	Pressure (bar)	Temp. (°C)	Surface speed (m/sec)
	FCS-PS08	PU-D57/NBR PTFE/NBR	600	-25 bis 100	5 15
	FCS-PS08A	PU/NDR PU-D57/NBR PTFE/NBR	250 400 400	-25 to 100	1 5 15
	FCS-PS08B	PU-D57/NBR PTFE/NBR	600	-25 to 100	5 10
	FCS-PS08C	PTFE/NBR	400	-25 to 100	2
	FCS-PS08D	PTFE/NBR	400	-25 to 100	3
	FCS-PS08E	PU-D57/NBR PTFE/NBR	600	-25 to 100	5 10
	FCS-PS08F	PU-D57/NBR PU/NBR	400 250	-25 to 100	5 1
	FCS-PS81	PU-D57/NBR PTFE/NBR	600	-25 to 100	5 10
	FCS-PS81B	PU-D57/NBR PTFE/NBR	600	-25 to 100	5 10
	FCS-PS09	PU/NBR/POM	400	-25 to 100	0,5
	FCS-PS09A	PTFE/NBR/POM	400	-25 to 100	1
	FCS-PS16	PU NBR	160	-30 to 105 -25 to 100	0,5
	FCS-PS16A	PU NBR	160	-30 to 105 -25 to 100	0,5
	FCS-PS17	PU/POM NBR/POM	400 250	-25 to 100	0,5
	FCS-PS17A	PU/POM NBR/POM	400 250	-25 to 100	0,5
	FCS-PS17B	PU/POM NBR/POM	400 250	-25 to 100	0,5
	FCS-PS19	PTFE-virgin / V-spring PTFE-Filled / V-spring	200 400	-200 to 260	15
	FCS-PS19A	PTFE-virgin / V-spring PTFE-Filled / V-spring	200 400	-200 to 260	2
	FCS-PS20	NBR/POM	700	-25 to 100	0,5
	FCS-PS23	PU/NBR/POM	400	-25 to 100	0,5
	FCS-PS35	PU	400	-30 to 105	0,4